(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 29 January 2004 (29.01.2004)

PCT

(10) International Publication Number WO 2004/008983 A 1

(51) International Patent Classification⁷: A61C 8/00, A61F 2/02, A61L 27/06

(21) International Application Number:

PCT/SE2003/000721

(22) International Filing Date: 6 May 2003 (06.05.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 0202272-1 19 July 2002 (19.07.2002) SE

(71) Applicant (for all designated States except US): ASTRA TECH AB [SE/SE]; Aminogatan 1, S-431 21 Mölndal (SE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): PETERSSON, Ingela [SE/SE]; Godhemsgatan 22A, S-414 68 Göteborg (SE). JUNEMO-BOSTRÖM, Kristina [SE/SE]; Barefjällsgatan 3, S-415 06 Göteborg (SE). JOHANS-SON-RUDÉN, Gunilla [SE/SE]; Bergstigen 20, S-436 42 Askim (SE). ANDERSSON, Fredrik [SE/SE]; Brogatan 2B, S-431 30 Mölndal (SE). HANSSON, Stig [SE/SE]; Gåsmossen 32, S-436 39 Askim (SE).

(74) Agent: AWAPATENT AB; Box 11394, S-404 28 Göteborg (SE).

- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: AN IMPLANT AND A METHOD FOR TREATING AN IMPLANT SURFACE



(57) Abstract: The invention relates to a method for treating an implant surface intended for implantation into bone tissue comprising providing fluorine/and/or fluoride on at least a part of the implant surface, and providing, on the implant surface, a microroughness having a root-mean-square roughness (R_q and/or S_q) of ≤ 250 nm and/or comprising pores having a pore diameter of ≤ 1 μ m and a pore depth of ≤ 500 nm. The invention also relates to an implant comprising a surface having the above characteristics.



WO 2004/008983 A1



European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM,

KE. LS. MW. MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM. AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

of inventorship (Rule 4.17(iv)) for US only

Published:

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.